

Physical Properties	
Flammability Rating	UL-224, VW-1
Recommended Cutting	Scissor
Colors	11
Tensile Strength PSI (ASTM D-638) lbs.	1,500
Elongation % (ASTM D-638)	200
Specific Gravity (ASTM D-792)	1.35
Low Temp. Flex (MIL-DTL-23053)	No Cracking
Heat Shock (MIL-DTL-23053)	No Cracking
Secant Modulus PSI (MIL-DTL-23053)	25,000
Longitudinal Change %(MIL-DTL-23053)	+/- 5
Moisture Absorption % (ASTM D-570)	.5

Operating Temperatures	
Minimum Continuous	-67°F/-55°C
Maximum Continuous (MIL-I-23053)	275°F/135°C
Melt (ASTM D-2117)	392°F/200°C

Electric	
Dielectric Strength (ASTM D-149; V/Mil)	500
Volume Resistivity (ASTM D-257; ohm-cm)	1.0x10 ¹⁴

Other Information	
RoHS	Yes
UL/CSA	Yes