

Kable Kontrol® 2:1 Thin Wall Heat Shrink Tubing - Polyolefin

Technical Specifications

Part Number	Inside Diameter		After Recovery		Operating Temperature	Length (Feet)	Color
	inch	mm	Internal Diameter Max (mm)	Wall Thickness Nom (mm)			
HS359-TW	1/4	6	3	0.56±0.10	-55°C to 125°C	250 Feet	Clear Black
HS363-TW	3/8	9	4.5	0.56±0.10	-55°C to 125°C	200 Feet	Clear Black
HS364-TW	1/2	12	6	0.56±0.10	-55°C to 125°C	200 Feet	Clear Black
HS365-TW	5/8	15	7.5	0.70±0.10	-55°C to 125°C	200 Feet	Clear Black
HS367-TW	3/4	18	9	0.70±0.10	-55°C to 125°C	200 Feet	Clear Black
HS368-TW	1-14	30	15	1.00±0.15	-55°C to 125°C	100 Feet	Clear Black
HS369-TW	1-1/2	40	20	1.00±0.15	-55°C to 125°C	100 Feet	Clear Black

Property	Test Method	Typical Performance
Tensile strength (MPa)	ASTM D 2671	≥10.4
Ultimate elongation (%)	ASTM D 2671	≥200
Tensile strength after heat aging (MPa)	158°C×168h	≥7.3
Ultimate elongation after heat aging (%)	158°C×168h	≥100
Longitudinal change (%)	ASTM D 2671	-5% ~ +5%
Flammability	ASTM D 2671 C method	VW-1
Dielectric strength (kV/mm)	ASTM D 149	≥15
Volume resistivity (Ω.cm)	ASTM D 876	≥10 ¹⁴