

Kable Kontrol® Heat Shrink End Caps
Technical Specifications

Part Number	As Supplies			After Recovery	
	Inner Diameter (Min)	Wall Thickness (±20%)	Height (±5)	Inside Diameter (Max)	Wall Thickness (±10%)
HSEC21-050-BK	1/2" (12mm)	0.9mm	45mm	5mm	2.5mm
HSEC21-075-BK	3/4" (20mm)	1mm	70mm	8.5mm	2.5mm
HSEC21-100-BK	1" (25mm)	1mm	80mm	11mm	2.5mm
HSEC21-150-BK	1-1/2" (40mm)	1.1mm	95mm	18mm	2.6mm
HSEC21-200-BK	2" (55mm)	1mm	125mm	26mm	2.7mm
HSEC21-300-BK	3" (75mm)	1.3mm	145mm	31mm	3.2mm

Property	Test Method	Standard Value
Tensile Strength	ASTM-D-638	≥12MPa
Elongation at Break	ASTM-D-638	≥300%
Tensile Strength after Aging	ASTM-D-638	≥10MPa (130°C,168 hrs)
Elongation at Break after Aging	ASTM-D-638	≥230% (130°C,168hrs)
Volume Resistivity	IEC 60093	≥1×10 ¹³ Ω·cm
Dielectric Strength	IEC 60243	≥15kV/mm
Brittle temperature	ISO 974	≤-40°C