

Technical Specifications

Property	Test Method	Standard
Tensile Strength(MPa)	ASTM D2671	19
Elongation(%)	ASTM D2671	200
Cold impact (-65°C)	ASTMD 2671 Method C	No cracking
Flammability	ASTM D2671	VW-1
Dielectric strength(kV/mm)	VDE 0303 Part2	26
Volume resistivity(Ω .cm)	VDE 0303 Part2	1.0×10^{14}

Inside Diameter	As Supplied (mm)	Recovered (mm)	
	Inner Diameter	Inner Diameter	Wall Thickness
3mm (1/8")	3.0±0.3	≤1.65	0.20±0.05
4.5mm (3/16")	4.5±0.3	≤2.35	0.20±0.05
6mm (1/4")	6.0+0.5/-0.3	≤3.10	0.25±0.05
8mm (5/16")	8.0+0.5/-0.3	≤4.10	0.25±0.05