

TECHNICAL SPECIFICATIONS

Property	Test Method	Standard
Tensile Strength(MPa)	ASTM D2671	19
Elongation(%)	ASTM D2671	200
Cold impact (-65°C)	ASTMD 2671 Method C	No cracking
Flammability	ASTM D2671	VW-1
Dielectric strength(kV/mm)	VDE 0303 Part2	26
Volume resistivity(Ω .cm)	VDE 0303 Part2	1.0×10^{14}

Inside Diameter	As Supplied (mm)	Recovered (mm)	
	Inner Diameter	Inner Diameter	Wall Thickness
3mm (1/8")	$3.0 \pm 0.8 / -0.3$	≤ 0.75	0.30 ± 0.05
4.5mm (3/16")	$4.5 \pm 0.8 / -0.3$	≤ 1.12	0.30 ± 0.05
6mm (1/4")	$6.0 \pm 0.8 / -0.3$	≤ 1.50	0.30 ± 0.05
9.5mm (3/8")	$9.5 \pm 0.8 / -0.3$	≤ 2.40	0.30 ± 0.05